The Assistant Engineer (QC)
Quality Control Lab, DUSIB
Vikas Kutir, ITO, New Delhi

D:1569

R.NO: 786

RECEIVED 10 JUL 2017

Part I

No. DUS 69/Ast/C10/DUSIB Date: 10-7-17

Sub: Testing of Bricks/Bricks tiles for Dimension/Compressive Strength.

W.O.NO. WB/4321/PG/EEC-10/DUSIB/16-17/D-72 dated 19.05.2016

1. Name of work: C/O JSC PAY & USE
   S. Head:- C/O Jan Suvidha Complex in place of 10 No.FRP Cubical at JJ Camp,Block-Y,Loha Mandi near Danjivan Dharam Kanta ,Naraina in AC-30 (PID 00006556)
2. Detail from where sample is collected: Site.....
3. Name of Circle/Division: . Circle-4, [redacted] C-10.....
4. Name of Junior Engineer: .. ...N/A.....
5. Name of Assistant Engineer: ...Ashwani Kumar....
6. Name of Executive Engineer: ...Shyam Singh.....
7. Name of Contractor/Agency: M/S Gupta Enterprises
8. Name of Officer collecting sample: Ashwani Kumar .....
9. **Date of collection/Date of filling frog** 5/7/17/6/7/17 - 10/7/17
10. **Date of Testing:** .....10/7/17.....
11. **Identification Mark:** ...ANTILL.....
12. **Class designation:** .....75.....
13. **No. of specimen sent for testing:** .....5-20 nos.....

Specimen relating to work mentioned above is/are sent for testing. It is certified that the sample (S) marked...sign by A.E..... has/have been taken in my presence which represent..... quantity of work/supply made at site/store.

Twelve Bricks

Signature of JE Incharge of work | **Signature of Contractor** | **Signature of Officer taking sample (EE/AE)**

Part II

TEST REPORT

No. SE (QC)/AE (Lab)/2017/D- 0915 Date : 12/07/17
Test No. 786 Date 10.7.17
Date of Receipt 10.7.17
Date of Testing 10.7.17

S. No.	Dimensions Length (cms)	Width (cms)	Area (sq.cm)	Maximum Strength Failure (T)	Compressive Strength failure (kg/sq.cm)	Average Compressive Strength ka/sq.cm
1.	22.40	11.00	= 246.40	23.00	93.34	90.53
2.	22.00	11.00	= 242.00	21.00	86.78	
3.	22.50	11.00	= 247.50	23.00	92.93	
4.	22.00	11.00	= 242.00	20.00	82.64	
5.	22.50	11.00	= 247.50	24.00	96.97	

ACCEPTABLE

DEMENSION TEST; FOR 20 BRICKS

1. **Length** :
2. **Width** : — NOT ASKED FOR —
3. **Height** :

Tested in my presence

Only testing has been conducted in this laboratory, the samples have been collected, cured, and handed over by the filed staff of the concerned division.

Copy to:
3. EE/C-10
4. .....
O/C

10/7/17

Assistant Engineer (QC) Lab.
DUSIB, Vikas Kutir, ITO

Assistant Engineer (QC)
Delhi Urban Shelter Improvement Board
Govt. of N.C.T. of Delhi
ITO, New Delhi-02