To

The Assistant Engineer(QC)
Quality Control Lab., DUSIB
Vikas Kutir, ITO, New Delhi

3.75

R.No: 0065

13 APR 2018

Part I

Dispatch No D-48/EE C-5/DUSIB/2018 Date: 13/4/18

Sub: Testing of CC cubes of mix M-15 for 7/28 days Compressive Strength.

A.L. No. 02/WH/4945/EE C-5/DUSIB/2017-18 /D- 64 dt. 27.04.2017
Name of work: C/o JSC Pay & Use
S. H. : Const. of septic tank, boundary wall, platform and installation of 44 nos. WC Cabins for pre-fab JSC in JJ Basti at New Priyanka Camp Sarita Vihar (Opp. Temple)
(Project ID 000007857)
(Project ID 7857)

1. Details from where sample is collected ----------site----------
2. Name of Circle/Division ----------Circle-II/C-5----------
3. Name of Junior Engineer ----------Sh. Surender Kumar----------
4. Name of Assistant Engineer ----------Sh. K.M Goel----------
5. Name of Executive Engineer ----------Sh. S.K Varshney----------
6. Name of Contractor/Agency ----------Sh. Subhashwar Dayal----------
7. Name of Officer collecting sample: ----------Sh. K.M. Goel----------
8. Date of collection: ----------15/3/18----------
9. Date of testing: ----------13/4/18----------
10. Required strength: ----------150 kg/cm2----------
11. No. of specimen sent for testing: --3 Nos. ----------
12. Size of specimen: 15 X 15 X15 cm----------
13. Mark of specimen: ----------a1----------

Specimen relating to work mentioned above is/are sent for testing. It is certified that the sample/ samples marked------a1--has/have been taken in my presence which represent---------quantity of works/supply made at site/store.

Signature of J.E
In charge of work

Signature of Contractor

Signature of Officer
taking sample (EE/AE)

Part II **TEST REPORT**

No. SE(QC)/AE(Lab.)/2018 /D- 674 Date: 16/04/18
Test No. 0065 Date: 13/04/18
Date of Receipt: 13/4/18
Date of testing: 13/4/18
Concrete Mix: M-15 Days test: 28 days

S. No	Wt. of specimen in gms	Area in ~~sq.cm.~~ mm2	Compressive Strength: Load kN ~~(Tonnes)~~	Compressive Strength: Comp. strength ~~(Kg./sq.cm)~~ N/mm2	Average Strength ~~(Kg./sq.cm)~~ N/mm2	Remarks
1.	8393gm	22500	435	19.33	19.55 N/mm2	
2.	8440 "	22500	442	19.64		
3.	8466 "	22500	443	19.69		

Tested in my presence

Only testing has been conducted in this laboratory. The sample/samples has/~~have~~ been collected and handed over by the field staff of the concerned division.

13/4/18
Assistant Engineer (QC-Lab)
DUSIB, Vikas Kutir,ITO

Assistant Engineer (QC)
Delhi Urban Shelter Improvement Board
Govt. of N.C.T. of Delhi
ITO, New Delhi-02

Copy to:- EE/C-5
1.
2. O/C