R.No: 2049
RECEIVED 18 JAN 2017

The Assistant Engineer (QC)
Delhi Urban Shelter Improvement Board
Vikas Kutir, ITO- New Delhi.

PART-I D/1248/EE C-5/DUSIB/2012 Dt 17/01/17
A. L. No. 02/WH/4945/ EE C-5/DUSIB/2016-17/D-28 Dated: 06.04.2016 (PID 6809)

Sybject:- Testing of CC Cubes of mix M-15 .....for 7 /28 days compressive strength.

Name of work :- P/L CC Pavement and repair of drains in JJC Shastri Market Moti Bagh South.

1.	Details from where sample is collected:-	From Site of work
2.	Name of Circle / Division:-	Circle-II /C-5
3.	Name of Junior Engineer:-	----------
4.	Name of Assistant Engineer :-	Sh. S.K. Mittal
5.	Name of Executive Engineer :-	Sh. S.K.Varshney
6.	Name of Contractor / Agency:-	DK Construction Co.
7.	Name of officer collecting sample:-	S-K Mittal
8.	Date of collection :-	16/12/16
9.	Date of testing :-	18/1/17
10.	Identification mark :-	
11.	Size of specimen :-	15x15x15 cm
12.	No. of Specimen sent for testing:-	3 Nos.
13.	Required strength :-	150 kg/sqcm

Specimen relating to work mentioned above is/are sent for testing. It is certified that the sample (s) marked.....has / have been taken in my presence which represent .....quantity of work / supply made at site.

Signature of JE Signature of contractor Signature of AE /EE

PART-II TEST REPORT

No. SE(QC) /AE (Lab) / 2017 /D-4008 Date:- 18/1/17
Test No. 2049 Date 18.1.17
Date of Receipt 18.1.17
Date of Testing :- 18.1.17
Concrete Mix :- M-15 Day test :- 28/31 days

S.No	Weight of specimen (Gms)	Area in Sqm.	Compressive Strength Load (Tones)	Comp. strength (Kg./sq.cm)	Average strength Kg./sqcm.	Remarks
1	7968	225	42.00	186.67	189.63	
2	8074	225	44.00	195.56		
3	8017	225	42.00	186.67		

EE may correlate accordingly

Tested in my presence

Only testing has been conducted in this laboratory. The sample(s) has / have been collected and handed over by the field staff of concerned division.

Copt to.
1. EE/C-5
2.....
d/c

18/1/17
Assistant Engineer (QC) Lab./ DUSIB
Assistant Engineer (QC)
Delhi Urban Shelter Improvement Board